



# Fine Aluminum Surfaces

Interior non-corrosive applications

	Photometric Properties				Mechanical Properties				
Product Name	Minimum Total Reflecto	Image Clarity DI	% Diffuse Reflection	Specular Reflection (Min.)	Hardness	Tensile ( Ksi )	Yield ( Ksi )	Sheet Size	Surface Finish
<b>LED &amp; Fluorescent Applications</b> <b>Anolux MIRO-SILVER<sup>®</sup> &amp; Anolux MIRO<sup>®</sup></b> PVD Enhanced <sup>®</sup> Surface Qualities									
Anolux Miro-SILVER <sup>®</sup> 4270AG	98 %	97	< 6	94 %	Hard	23.2-29.0	20.3-26.1	.020 X 49.212" X 96"	Silver PVD Enhanced™ Specular Mirror Finish
Anolux Miro-SILVER <sup>®</sup> 2000AG	97 %	97	< 97	95 %	½ Hard	23.2-29.0	20.3-26.1	.020 X 49.212" X 96"	Silver PVD Enhanced™ Scattergloss Mirror Finish
Anolux Miro <sup>®</sup> IV	95 %	95	< 12	90 %	Hard	23.2-29.0	20.3-26.1	.020 X 48.500" X 96"	PVD Enhanced™ Specular Mirror Finish
Anolux Miro <sup>®</sup> IV** 4428GP	95 %	95	< 12	90 %	Hard	23.2-29.0	20.3-26.1	.016 X 48.500" X 24"	PVD Enhanced™ Specular Mirror Finish
Anolux Miro <sup>®</sup> Stucco	95 %	n.m.	94	•	Hard Rolled	23.2-29.0	21.8-27.6	.012 X 49.212" X 96" .020 X 49.212" X 96"***	PVD Enhanced™ Embossed Specular Mirror Finish
Anolux Miro <sup>®</sup> 5011GP**	94 %	n.m.	80-90	•	Hard	23.2-26.9	21.8-25.4	.020 X 49.212" X 96"	PVD Enhanced™ Diffuse Matt Finish
Anolux Miro <sup>®</sup> 2000GP**	94 %	93	< 93	94 %	½ Hard	23.2-29.0	20.3-26.1	.020 X 49.212" X 96"	Silver PVD Enhanced™ Scattergloss Mirror Finish
<b>White</b> <b>LED &amp; Fluorescent Applications</b> Diffuse & Reflective White Grades									
Whitelite <sup>®</sup> 92	92 %	•	•	•	H-14	23.0	20.0	.020 X 48" X 96" .040 X 48" X 96"***	High Reflectance Gloss Painted Aluminium
Whitelite <sup>®</sup> 82	82 %	•	•	•	H-14	23.0	20.0	.020 X 48" X 96" .040 X 48" X 96"	White Painted Aluminium
WhiteOptics™ - F16	98	•	•	•	•	•	•	.009 X 48" X 24"	High Reflectance Film
MIRO-White <sup>®</sup> - M16A6	98	•	•	•	H-14	23.0	20.0	.023 X 48" X 24" custom sizes available**	High Reflectance Film on Aluminium
MIRO-White <sup>®</sup> - M16F8	98	•	•	•	H-14	23.0	20.0	.025 X 48" X 24" custom sizes available**	High Reflectance Film on Steel
<b>UV – Hydroponic – Fluorescent Applications</b> <b>Anolux<sup>®</sup></b> Anodized Reflective Surface Qualities									
Anolux <sup>®</sup> I	86 %	93	< 20	72 %	Hard	23.2-29.0	20.3-26.1	.020 X 49.212" X 96"	Specular Mirror Finish
Anolux <sup>®</sup> III	86 %	94	< 14	83 %	½ Hard	14.5-20.3	10.2-16.0	.032 X 48.500" X 24"	Specular Mirror Finish
Anolux <sup>®</sup> UVS**	86 %	92	15-22	72 %	Hard	18.9	16.0	.020 X 49.212" X 96" .040 X 49.212" X 96"***	Specular Mirror Finish
Anolux <sup>®</sup> 600G**	86%	28-56	65-72	•	½ Hard	21.8–26.9	20.3–25.4	.020 X 49.212" X 96"	Semi Specular Finish
Hammertone	86 %	•	86	•	Hard Rolled	23.2-29.0	21.8-27.6	.020 X 49.212" X 96" .025 X 49.212" X 96"	Embossed Finish
Pebbletone	86 %	•	86	•	Hard Rolled	23.2-29.0	21.8-27.6	.020 X 39.370" X 96"	Embossed Finish
<b>DeZine<sup>®</sup></b> Decorative Surface Qualities									
DeZine <sup>®</sup> Copper Brite**	•	•	•	•	Hard	25.2-26.3	19.4-20.7	.025 X 48.500" X 24" custom sizes available**	Specular Mirror Copper Finish
DeZine <sup>®</sup> Specular Gold**	•	•	•	•	Hard	24	23	.020 X 49.212" X 24" custom sizes available**	Specular Mirror Gold Finish
DeZine <sup>®</sup> Golden Grow <sup>®</sup>	72 %	•	50-60	•	Hard Rolled	24	23	.020 X 49.212" X 96"	Embossed Specular Gold Finish

Standard inventory changes without notice.

\*\*Minimum production requirements apply.

Technical Inspection Reports are only available upon request – charges may apply.

**Slit Coil & Custom Blank Sizes available upon request - minimum order requirements apply**

Treatments to the surface finish or use in an exterior application is done at the user's own risk and liability